



L&A COATINGS

"Passionate about Paint"

TECHNICAL DATA SHEET

Product:

Rapi-Liner® 110 – High Build Epoxy Novolac
DTM Coating (FDA compliant)

Product Description & Suggested Uses:

RAPI-LINER® 110 Liner is a two-component (2K), Novolac-modified Epoxy liner designed for direct-to-metal (DTM) applications where excellent corrosion, chemical, and abrasion resistance are required. All RAPI-LINER® 110 ingredients are food-grade and meet FDA 21 CFR 175.300 for direct food contact. RAPI-LINER® 110 is especially suitable for metal tank liner applications for commodities such as flour, sugar, plastic pellets, grain, corn syrup, and calcium carbonate.

Mixing and Thinning/Reducing Instructions:

Prepare RAPI-LINER® 110 Liner by mixing RAPI-LINER® 110 Resin (Part A) 1:1 by volume with RCT 01 1228 AM Hardener (Part B). Agitate each component thoroughly before combining and then agitate mixture. No reduction is necessary. If reducing or thinning is required, contact your Love & Associates (L&A) technical service representative for instructions.

Directions for Use:

Surface must be clean, dry, sound, and free of dirt, dust, grease, oils, residues, waxes, water, foreign particles, and any other contaminants that may interfere with coating adhesion and intimate contact with substrate. Prepare the substrate by abrasive blasting to a profile of 2.0-4.0 mils per NACE SSPC - SP10. Metal surface must be 5 degrees above the dew point temperature.

RAPI-LINER® 110 Liner is designed to be applied with airless spray @ 3000-4000 psi and 0.017-0.030 tips. Pot life is 4 hours @ 75°F and significantly reduced at elevated temperatures.

Clean-up:

Clean all equipment immediately after use with MEK or other L&A approved solvents. Use clean solvent only. In case of spill, absorb and dispose of in accordance with local, State, and/or Federal regulations.

Storage & Shelf Life:

Store indoors in original, tightly sealed container out of direct sunlight between 40°F (5°C) and 100°F (38°C), 0% to 90% relative humidity. Warranted shelf life is 12 months from date of manufacture (DOM) in original unopened and properly stored container.

Typical Mixed Properties:

Appearance	Light Blue, Salmon, or White
Type	Novolac Epoxy
Viscosity (25°C)	90-95 (KU's)
Specific Gravity (25°C)	1.30-1.40
Density (25°C)	10.8-11.7 lbs/gal
% Solids (by Volume)	80-82%
% Solids (by Weight)	85-87%
VOC	0.1-0.15 lbs/gal
VOC (less water/exempt)	0.1-0.12 lbs/gal
Flash Point	-15°C (5°F)
Gloss	Full
Recommended DFT	8-12 mils (200-300 um)
Maximum DFT	18 mils (450 um)
Coverage	1325 ft ² @ 1.0 mil
Dry @ 75 degrees F	3-4 hrs touch 6-7 hrs handle 96 hrs in service as a Liner
Force Cure	160-200°F for 2.0 hrs In service – 24 hrs
Recoat	Within 96 hrs

Packaging:

RAPI-LINER® 110 Liner is available in one 1-gallon cans, five 5-gallon pails, and 55-gallon steel drums. For additional packaging options, please contact your local L&A representative.

Safety Information:

Avoid contact with skin and use good ventilation. Wear chemically resistant gloves (nitrile are recommended) and chemical safety glasses. If skin contact is made, wash immediately with soap and water. Do not use solvents to clean skin. Refer to Safety Data Sheet for further safety and handling information.

FOR PROFESSIONAL USE ONLY
NOT FOR RESIDENTIAL USE
KEEP OUT OF REACH OF CHILDREN

Physical Performance Properties:

LOVE & ASSOCIATES, LLC | 3922 WEST LOOP 281, SUITE A, LONGVIEW, TX 75604 | (903) 759-2234 | WWW.LOVEASSOCIATES.NET

Warranty & Limitation of Seller's Liability

All statements made on any product, product label, product manual, product data sheet(s), technical data chart(s) contained herein, are accurate to the best of our knowledge. The product(s) and information are intended for use by trained persons having skill and knowledge in the industry at their own discretion and risk. Love & Associates, LLC warrants only that its coatings, resins, inks and/or adhesives represented herein meet the formulation standards of Love & Associates, LLC. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY THE SELLER, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OR LAW, OR OTHERWISE INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Note that workmanship, weather, construction equipment, quality of other materials and other variables affecting the results and performance are beyond our control. No agent, employee, or representative of seller has any authority to bind seller to any affirmation, representation or warranty except as stated above.



L&A COATINGS

"Passionate about Paint"

TECHNICAL DATA SHEET

Product:

Rapi-Liner® 110 – High Build Epoxy Novolac
DTM Coating (FDA compliant)

Test	Test Method	Result
Adhesion	ASTM D3359	5A
Pencil Hardness	ASTM D3363	4H-5H
Abrasion resistance	ASTM D4060	1000 cycles, 100 mg loss
Bend – Flexibility	ASTM D522	Passes 1.5 inch radius bend
Impact	ASTM D2794	40 in/# Direct
Salt Fog	ASTM B117	3000 hours
Humidity	ASTM 4585	3000 hours
Heat Resistance	NACE SPO302	Dry Continuous – 400F Dry Intermittent – 500F Immersed Continuous- 140F Immersed Intermittent – 200F
Thermal Shock Resistance w/ Crude Oil	NACE SPO302	10 cycles of 24 hours @ 325F followed by 24 hours @ -40F No adhesion loss, cracking or flaking

Warranty & Limitation of Seller's Liability

All statements made on any product, product label, product manual, product data sheet(s), technical data chart(s), or specification chart(s) contained herein, are accurate to the best of our knowledge. The product(s) and information are intended for use by trained persons having skill and knowledge in the industry at their own discretion and risk. Love & Associates, LLC warrants only that its coatings, resins, inks and/or adhesives represented herein meet the formulation standards of Love & Associates, LLC. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY THE SELLER, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OR LAW, OR OTHERWISE INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Note that workmanship, weather, construction equipment, quality of other materials and other variables affecting the results and performance are beyond our control. No agent, employee, or representative of seller has any authority to bind seller to any affirmation, representation or warranty except as stated above.