



LOVE & ASSOCIATES

MANUFACTURERS OF
INDUSTRIAL COATINGS

TECHNICAL
DATA SHEET

19 – 86 LIGHT GRAY FAST DRY ALKYD PRIMER

DESCRIPTION: 19 – 86 Lt. Gray Fast Dry Alkyd Primer provides super fast dry with excellent protection of steel surfaces through corrosion resistance and improved adhesion of the primer-topcoat system. 19 – 86 Lt. Gray Fast Dry Alkyd Primer is formulated to a specific pigment volume concentration in order to maximize impermeability and adhesion, while providing a good surface for 14 – Series topcoats.

TYPICAL USES INCLUDE

Storage Tanks and Piping
Machinery and Equipment

Structural Steel
Marine Vessels

Buildings, Trucks, and Trailers
General Purpose Shop Primer

TYPICAL PHYSICAL PROPERTIES:

COLOR:	Lt. Gray	RECOMMENDED D.F.T.:	1.5 – 2 mils
COMPONENTS:	One	DRY TIME:	@ 77° F, 55% R.H.
GLOSS:	Flat	To Touch:	5 - 10 Minutes
MIXING RATIO (BY VOL.):	N/A	To Handle:	1 Hour
WT./GALLON:	10.4 lbs	To Recoat:	30 – 60 Minutes
POT LIFE:	N/A	THINNING:	Brush: T-43 (not normally recommended)
VISCOSITY AT 77° F:	68 KU		Spray: T-42 (0-10%)
SHELF LIFE:	2 Years	APPLICATION METHODS:	Spray, Dip, Electrostatic Spray
SOLIDS BY WEIGHT:	57.9%	FILM THICKNESS:	
TEMP. RESISTANCE:	225° F	Wet:	4.0 – 5.5 mils
SOLIDS BY VOLUME:	38.63%	Dry:	1.5 – 2.0 mils
CHEM. RESISTANCE:	Moderate	APPLICATION EQUIPMENT:	
THEORETICAL COVERAGE:	618 ft ² /gal @ 1 mil dft	CONVENTIONAL:	DeVilbiss 510 Gun E Tip + Needle, 704 Air Gap
FLASH POINT:	81° F, TCC	AIRLESS:	Graco 30:1 Pump, 613 Tip or equivalent
V.O.C.:	4.5 lbs/gal	CLEANING OF EQUIPMENT:	T-42 or Xylene

**PACKAGING:**

1 Gallon Cans

5 Gallon Pails

55 Gallon Drums

APPLICATION CONDITIONS:

Surface should be dry, above 40° F and at least 5° F above the dew point.

SURFACE PREPARATION:

Remove all grease, oil, dirt, dust or other contaminants.

PREFERRED: SSPC–SP6 Commercial Blast Cleaning

MINIMUM: SSPC–SP2 and 3 Hand and Power Tool Cleaning

PREVIOUSLY PAINTED SURFACES:

Remove all grease, oil, dirt, dust or other contaminants by Hand or Power Tool Cleaning. Surface must be clean and dry, SSPC–SP2 or 3 or Brush-Off Blast Cleaning SSPC-SP7. Spot prime all bare areas.

RECOMMENDED TOP COAT:

Alkyd Enamels, specifically 13 and 14 – Series Enamels.

SAFETY INFORMATION**DOT CLASSIFICATION: PAINT UN 1263**

DANGER: Causes eye burns and skin irritation. Vapor harmful. Dried film of this paint may be harmful if eaten or chewed. Contains organic solvent. Do not get in eyes, on skin or on clothing. Wear eye protective equipment when handling. Keep away from heat, sparks, and flame. Avoid breathing vapor or mist. Wash thoroughly after handling. Wear appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after application unless air monitoring demonstrates vapor/mist levels are below applicable level. Follow respirator manufacturer's directions for use. Keep container closed. Keep out of reach of children.

FIRST AID: IN CASE OF EYE CONTACT, IMMEDIATELY FLUSH EYES WITH PLENTY OF WATER FOR AT LEAST 15 MINUTES. CALL A PHYSICIAN. FOR SKIN CONTACT, FLUSH WITH WATER AND WASH WITH SOAP AND WATER. REMOVE CONTAMINATED CLOTHING AND LAUNDER BEFORE REUSE. IF INHALED, REMOVE TO FRESH AIR. IF NOT BREATHING GIVE ARTIFICIAL RESPIRATION, PREFERABLY MOUTH-TO-MOUTH, AND CALL A PHYSICIAN.

NOTICE: Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or **fatal**.

FOR INDUSTRIAL USE ONLY