

PRODUCT:
1227PT HS HB 2.5 DTM Epoxy

Product Description & Suggested Uses:

1227PT is a Pre-Thinned (PT) ready to use two component, epoxy polyamide designed for applications where excellent corrosion, chemical, moisture and water barrier properties are required.

Benefits Includes:

- Single Coat Direct to Metal High Build
- Low VOC & Very Low HAPS
- Very Good Gloss & Color Retention

Typical Uses:

- Railcar Exteriors
- Tank Exteriors
- Structural Steel
- Carbon Black Interiors

Mixing and Thinning/Reducing Instructions:

Mix 1 part 1227PT by volume with 1 part 1227-000PT Hardener. Agitate each component thoroughly before combining. If reducing or thinning is required, please contact your Love & Associates technical service representative for instructions.

Directions for Use:

Surface must be clean, dry, sound and free of dirt, dust, grease, oils, residues, waxes, water, foreign particles, and any other contaminants that may interfere with coating adhesion and intimate contact with substrate. Steel surface preparation should meet SSPC-SP6/NACE 3. Metal surface must be 5 degrees above the dew point temperature.

1227PT is designed to be applied by airless spray, brush or roll. Airless spray @ 2500-4500 psi with 0.017-0.021 tips is recommended. If reduction is required, 5-10% with an L&A recommended solvent may be used after both components are mixed together. Pot life is 6 hours @ 75 degrees and significantly reduced at elevated temperatures. Pot life is extended with reduction.

Force Dry: 1 hour minimum air dry @ 75°F, then force dry @ 140°F for 1 hour.

Clean-up:

Clean all equipment immediately after use with MEK or other L&A approved solvents. Use clean solvent only. In case of spill, absorb and dispose of in accordance with local, State, and/or Federal regulations.

Typical Mixed Properties:

Color – Black, White, 7035 & 7044 Gray
Type – Epoxy/Polyamide
Viscosity (25°C) – 60-70 Ku's
Density (25°C) – 9.5#/gl (1.14 s.g.)
% Solids (by Volume) – 65-67%
% Solids (by Weight) – 74-76%
VOC – 2.2-2.5 #/gl
Flash Point = 50°F
Gloss - >80°
Recommended DFT – 6-8 mils (150-200 um)
Maximum DFT - 12 mils (300 um) per coat
Coverage – 1058 sqft/gl @ 1.0 mil
Dry @ 75 degrees F – 2-3 hours to touch
4-6 hours to handle
Recoat @ 75°F – 12 hours min, 7 days max
Pot life @ 75°F – 6 hours
Salt Fog – ASTM B117
1500 hrs No Blistering or Rusting

Packaging:

1227PT is available in one 1-gallon cans, five 5-gallon pails, 55-gallon steel drums and totes. For additional packaging options, please contact your local Love & Associates representative.

Storage & Shelf Life:

Store indoors in original, tightly sealed container out of direct sunlight between 40°F (5°C) and 100°F (38°C), 0% to 90% relative humidity. Warranted shelf life is 12 months from date of manufacture (DOM) in original unopened and properly stored container.

Safety Information:

Avoid contact with skin and use good ventilation. Wear chemically resistant gloves (nitrile are recommended) and chemical safety glasses. If skin contact is made, wash immediately with soap and water. Do not use solvents to clean skin. Refer to Safety Data Sheet for further safety and handling information.

FOR PROFESSIONAL USE ONLY NOT FOR RESIDENTIAL USE
KEEP OUT OF REACH OF CHILDREN