



# L&A COATINGS

*"Passionate about Paint"*

# TECHNICAL DATA SHEET

## Product:

RCT 100G Liner – Glass Reinforced Novolac Modified Epoxy DTM Coating

### Product Description & Suggested Uses:

RCT 100G Liner is a two-component (2K), glass-filled Novolac Epoxy designed for direct-to-metal (DTM) applications where excellent corrosion, chemical, and abrasion resistance are required. It is especially suitable for metal tank liner applications requiring excellent resistance to hydrocarbons, alcohols, and petroleum products.

### Mixing and Thinning/Reducing Instructions:

Prepare RCT 100G Liner by mixing RCT 08 1003 EP Resin (Part A) 1:1 by volume with RCT 01 1140 AM Hardener (Part B). Agitate each component thoroughly before combining and then agitate mixture. No reduction is necessary. If reducing or thinning is required, contact your Love & Associates (L&A) technical service representative for instructions.

### Directions for Use :

Surface must be clean, dry, sound, and free of dirt, dust, grease, oils, residues, waxes, water, foreign particles, and any other contaminants that may interfere with coating adhesion and intimate contact with substrate. Prepare the substrate by abrasive blasting to a profile of 2.0-4.0 mils per NACE SSPC - SP10. Metal surface must be 5 degrees above the dew point temperature.

RCT 100G Liner is designed to be applied with airless spray @ 3000-4000 psi and 0.017-0.030 tips. Pot life is 2 hours @ 75°F and significantly reduced at elevated temperatures.

### Clean-up:

Clean all equipment immediately after use with MEK or other L&A approved solvents. Use clean solvent only. In case of spill, absorb and dispose of in accordance with local, State, and/or Federal regulations.

### Storage & Shelf Life:

Store indoors in original, tightly sealed container out of direct sunlight between 40°F (5°C) and 100°F (38°C), 0% to 90% relative humidity. Warranted shelf life is 12 months from date of manufacture (DOM) in original unopened and properly stored container.

### Typical Mixed Properties:

|                         |   |
|-------------------------|---|
| Appearance              | Light Green Liquid  |
| Type                    | Novolac Epoxy   |
| Viscosity (25°C)        | 90-95 (KU's)  |
| Specific Gravity (25°C) | 1.40-1.45   |
| Density (25°C)          | 12.0-12.5 lbs/gal   |
| % Solids (by Volume)    | 80-85%  |
| % Solids (by Weight)    | 90-95%  |
| VOC                     | 0.1-0.2 lbs/gal   |
| VOC (less water/exempt) | 0.6-0.8 lbs/gal   |
| Flash Point             | -17°C (0°F)   |
| Gloss                   | Semi  |
| Recommended DFT         | 8-12 mils (200-300 um)  |
| Maximum DFT             | 18 mils (450 um)  |
| Coverage                | 1325 ft <sup>2</sup> @ 1.0 mil                                  |
| Dry @ 75 degrees F      | 3-4 hrs touch<br>6-7 hrs handle<br>72 hrs in service as a Liner |
| Recoat                  | Within 72 hrs   |

### Packaging:

RCT 100G Liner is available in one 1-gallon cans, five 5-gallon pails, and 55-gallon steel drums. For additional packaging options, please contact your local L&A representative.

### Safety Information:

Avoid contact with skin and use good ventilation. Wear chemically resistant gloves (nitrile are recommended) and chemical safety glasses. If skin contact is made, wash immediately with soap and water. Do not use solvents to clean skin. Refer to Safety Data Sheet for further safety and handling information.

FOR PROFESSIONAL USE ONLY  
NOT FOR RESIDENTIAL USE  
KEEP OUT OF REACH OF CHILDREN

### Physical Performance Properties:

# TECHNICAL DATA SHEET

**Product:**

RCT 100G Liner – Glass Reinforced Novolac Modified Epoxy DTM Coating

| Test                | Test Method | Result  |
|---------------------|-------------|---|
| Adhesion            | ASTM D3359  | 5A  |
| Pencil Hardness     | ASTM D3363  | 4H-5H   |
| Abrasion resistance | ASTM D4060  | 5000 cycles, 150 mg loss  |
| Bend – Flexibility  | ASTM D522   | Passes 1.5 inch radius bend   |
| Impact              | ASTM D2794  | 50 in/# Direct  |
| Salt Fog            | ASTM B117   | 3000 hours  |
| Humidity            | ASTM 4585   | 3000 hours  |
| Heat Resistance     | NACE SPO302 | Dry Continuous – 400F<br>Dry Intermittent – 500F<br>Immersed Continuous- 140F<br>Immersed Intermittent – 200F |

|                                  |           |
|----------------------------------|-----------|
| 5% Salt Solution                 | Excellent |
| Ethanol & Methanol               | Excellent |
| Ethylene & Propylene Glycol      | Excellent |
| Mineral Spirits & Naptha         | Excellent |
| Gasoline, Diesel & Kerosene      | Excellent |
| Crude, Mineral & Motor Oil       | Excellent |
| Turpentine                       | Excellent |
| Hydrochloric Acid Sol'n (Acidic) | Good      |
| Sodium Hydroxide Sol'n (Caustic) | Good      |
| Hydrosulfuric Acid Sol'n         | Excellent |
| Ammonia                          | Excellent |
|                                  |           |
|                                  |           |

**Chemical Immersion Resistance: 12 months @ 140°F**