RAPID CURE TECHNOLOGIES

Technical Data Sheet

Product ID: Rapi-Liner® 100 – Novolac Modified Epoxy DTM

Document Date: 10 June 2019

Product Description & Suggested Uses:

RCT 100 Liner is a two component Novolac Epoxy designed for Direct to Metal applications where excellent corrosion and chemical resistance are required. It is especially suitable for Liner applications with excellent resistance to Hydrocarbons, Alcohols and Petroleum products.

Mixing and Thinning/Reducing Instructions:

Mix RCT 100 Liner 1:1 by volume with RCT 01 1140 AM Hardener. Agitate each component thoroughly before combining and then agitate mixture. No reduction is necessary. If reducing or thinning is required, please contact your Rapid Cure Technologies (RCT) technical service representative for instructions.

Directions for Use :

Surface must be clean, dry, sound and free of dirt, dust, grease, oils, residues, waxes, water, foreign particles, and any other contaminants that may interfere with coating adhesion and intimate contact with substrate. Prepare the substrate by abrasive blasting to a profile of 2.0-4.0 mils per NACE SSPC - SP10. Metal surface must be 5 degrees above the dew point temperature.

RCT 100 Liner is designed to be applied with airless spray @ 3000-4000 psi and 0.017-0.030 tips. Pot life is 2 hours @ 75 degrees and significantly reduced at elevated temperatures.

Clean-up:

Clean all equipment immediately after use with MEK or other RCT approved solvents. Use clean solvent only. In case of spill, absorb and dispose of in accordance with local, State, and/or Federal regulations.

Storage & Shelf Life:

Store indoors in original, tightly sealed container out of direct sunlight between 40°F (5°C) and 100°F (38°C), 0% to 90% relative humidity. Warranted shelf life is 12 months from date of manufacture (DOM) in original unopened and properly stored container.

Typical Mixed Properties:

Color	Green, Beige, Gray, Black, White
Туре	Novolac Epoxy
Viscosity (25°C)	90-95 (KU's)
Specific Gravity (25°C)	1.40-1.45
Density (25°C)	12.0-12.5 lbs/gal
% Solids (by Volume)	80-85%
% Solids (by Weight)	90-95%
VOC	0.1-0.2 lbs/gal
VOC (less water/exempt)	0.6-0.8 lbs/gal
Flash Point	-15°C (5°F)
Gloss	Full
Recommended DFT	10-12 mils (250-300 um)
Maximum DFT	18 mils (450 um)
Coverage	1325 ft ² @ 1.0 mil
Dry @ 75 degrees F	3-4 hrs touch
	6-7 hrs handle
	72 hrs in service as a Liner
Recoat	Within 72 hrs
Potlife	2 hours @ 75°F

Packaging:

RCT 100 Liner is available in one 1-gallon cans, five 5-gallon pails and 55-gallon steel drums. For additional packaging options, please contact your local Rapid Cure Technologies representative.

Safety Information:

Avoid contact with skin and use good ventilation. Wear chemically resistant gloves (nitrile are recommended) and chemical safety glasses. If skin contact is made, wash immediately with soap and water. Do not use solvents to clean skin. Refer to Safety Data Sheet for further safety and handling information.

FOR PROFESSIONAL USE ONLY NOT FOR RESIDENTIAL USE KEEP OUT OF REACH OF CHILDREN

RCT 08 1004 EP

RAPID CURE TECHNOLOGIES, INC. | 7030 FLY RD, EAST SYRACUSE, NY 13057 | (888) 847-3610 | WWW.RAPIDCURETECHNOLOGIES.COM

Warranty & Limitation of Seller's Liability

All statements made on any product, product label, product manual, product data sheets, technical data charts or specification charts contained herein, are accurate to the best of our knowledge. The products and information are intended for use by trained persons having skill and knowledge in the industry at their own discretion and risk. Rapid Cure Technologies, Inc. warrants only that its coatings, resins, inks and/or adhesives represented herein meet the formulation standards of Rapid Cure Technologies, Inc. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY THE SELLER, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OR LAW, OR OTHERWISE INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Note that workmanship, weather, construction equipment, quality of other materials and other variables affecting the results and performance are beyond our control. No agent, employee or representative of seller has any authority to bind seller to any affirmation, representation or warranty except as stated above.



Technical Data Sheet

Product ID: Rapi-Liner[®] 100 – Novolac Modified Epoxy DTM

Document Date: 10 June 2019

Physical Performance Properties:

Test	Test	Result
	Method	
Adhesion	ASTM	5A
	D3359	
Pencil	ASTM	4H-5H
Hardness	D3363	
Abrasion	ASTM	1000 cycles, 100 mg loss
resistance	D4060	
Bend –	ASTM	Passes 1.5 inch radius bend
Flexibility	D522	
Impact	ASTM	50 in/# Direct
	D2794	
Salt Fog	ASTM	3000 hours
	B117	
Humidity	ASTM	3000 hours
	4585	
Heat	NACE	Dry Continuous – 400°F
Resistance	SPO302	Dry Intermittent – 500°F
		Immersed Continuous- 180°F
		Immersed Intermittent – 200°F
Thermal	NACE	10 cycles of 24 hours @ 325°F
Shock	SPO302	followed by 24 hours @ -40°F
Resistance		
w/ Crude		No adhesion loss, cracking or
Oil		flaking

Chemical Immersion Resistance: 12 months @ 140F

Excellent
Excellent
Excellent
Excellent
Excellent
Excellent
Excellent
Good
Good
Excellent
Excellent

RAPID CURE TECHNOLOGIES, INC. | 7030 FLY RD, EAST SYRACUSE, NY 13057 | (888) 847-3610 | WWW.RAPIDCURETECHNOLOGIES.COM

Warranty & Limitation of Seller's Liability

All statements made on any product, product label, product manual, product data sheets, technical data charts or specification charts contained herein, are accurate to the best of our knowledge. The products and information are intended for use by trained persons having skill and knowledge in the industry at their own discretion and risk. Rapid Cure Technologies, Inc. warrants only that its coatings, resins, inks and/or adhesives represented herein meet the formulation standards of Rapid Cure Technologies, Inc. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY THE SELLER, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OR LAW, OR OTHERWISE INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Note that workmanship, weather, construction equipment, quality of other materials and other variables affecting the results and performance are beyond our control. No agent, employee or representative of seller has any authority to bind seller to any affirmation, representation or warranty except as stated above.